



Bumper Specialties, Inc.

ADHESIVE INFORMATION

BSI-95 Rubber Adhesive (Standard Adhesive)

ADHESIVE TYPE: Solvent Based, High Shear

SUBSTRATE: 2 mils polyester substrate on a 90 lb release liner, PE coated, bleached, super-bright white Kraft liner.

TYPICAL PROPERTIES		
Static Shear Test		300+ hours* [PSTC**-07 Procedure A / ASTM*** B 3654]
Quick Tack-Stainless Steel		144 oz/in ² (633 g/cm ²)
Peel Adhesion		160 oz/in (1785 g/cm) [PSTC-3** / ASTM*** D 3330]
Substrate:	Thickness	2 mils (50 microns)
	Basis Weight	10,000 in ² /lb (142,230 cm ² /kg) typical value
	Tensile Strength	28,000psi MD (1,900,000 g/cm ²)
Liner:	Thickness	6.2 mils (158 microns)
	Basis Weight	92.0 lb (151 g/m ²)
Temperature:	Application	65°F — 150°F (18°C — 65.6°C)
	End Use	0°F — 180°F (-18°C — 82.2°C)
Substrate Elongation		120% MD
Shelf Life		24 months based on accelerated aging
Storage		73.4°F (23°C) and 55% relative humidity

BSI-94 Acrylic Adhesive (Must be specified when ordering)

ADHESIVE TYPE: Solvent Based, Low Temperature, High Shear, Quick Stick

SUBSTRATE: 2 mils polyester substrate on a 90 lb release liner, PE coated, bleached, super-bright white Kraft liner.

TYPICAL PROPERTIES		
Static Shear Test		500+ hours* [PSTC**-07 Procedure A / ASTM*** B 3654]
Quick Tack-Stainless Steel		77 oz/in ² (338 g/cm ²)
Peel Adhesion		64 oz/in (714 g/cm) [PSTC-3** / ASTM*** D 3330]
Substrate:	Thickness	2 mils (50 microns)
	Basis Weight	10,000 in ² /lb (142,230 cm ² /kg) typical value
	Tensile Strength	28,000 psi MD (1,900,000 g/cm ²)
Liner:	Thickness	6.2 mils (158 microns)
	Basis Weight	92.0 lb (151 g/m ²)
Temperature:	Application	65°F — 150°F (18°C — 65.6°C)
	End Use	-40°F — 300°F (-40°C — 149°C)
Substrate Elongation		120% MD
Shelf Life		24 months based on accelerated aging
Storage		73.4°F (23°C) and 55% relative humidity

Adhesive testing for the acrylic and synthetic rubber was conducted using a polyester carrier. This information sheet is for typical values and is not a specification. End user assumes the responsibility for suitable testing and approval of this product's functionality. Adhesives are resistant to water and detergents. Not recommended for use with aliphatic or aromatic hydrocarbons.

Notice to Purchaser

Information and specifications contained herein are believed to be reliable, but no assurance is given as to the accuracy or completeness of technical information or recommendations. The Sellers or Manufacturers sole undertaking with respect to the product in lieu of all warranties of any kind is to replace any of the product that is proved to be defective. Neither Seller nor Manufacturer makes any warranty or representation the product is suitable for any specific purpose, nor shall Seller or Manufacturer be liable for any incidental or consequential damages for breach of any expressed or implied warranty. No person is authorized to assume for Seller or Manufacturer any liability or obligation in regard to this product other than as expressly set forth in this paragraph.

Materials used by Bumper Specialties, Inc. are in full compliance with the European Standard for RoHS.

*Maximum adhesion achieved after 24 hours **Pressure Sensitive Tape Council ***American Society for Testing and Materials